

表 7(续)

牌号	状态	板材厚度/mm	弯芯直径/mm	弯曲角 α/度
TA8	M	<1.8	4T	105
		1.8~4.75	5T	
TA8-1	M	<1.8	3T	
		1.8~4.75	4T	
TA9	M	<1.8	4T	
		1.8~4.75	5T	
TA9-1	M	<1.8	3T	
		1.8~4.75	4T	
TA10	M	<1.8	4T	
		1.8~4.75	5T	
TC4	M	<1.8	4T	
		1.8~4.75	5T	
TC4ELI	M	<1.8	4T	
		1.8~4.75	5T	
TB5	M	1.8~3.18	4T	
		>3.18	5T	
TB8	M	1.8~2.4	5T	
		>2.4	6T	
TA5	M	5~5.0	4T	60
		>5.0	5T	50
TA6	M	0.8~1.0	4T	40
		>1.0	5T	50
TA7	M	>2.0~5.0	4T	40
		>5.0	5T	40
TA13	M	0.5~2.0	3T	180
TA15	M	0.8~5.0	4T	30
		>5.0	5T	30
TA17	M	0.5~1.0	4T	80
		>1.0~2.0	5T	60
		>2.0~5.0	6T	50
TA18	M	0.5~1.0	3T	100
		>1.0~2.0		70
		>2.0~5.0		60
		>5.0		60
TB2	ST	1.0~3.5	4T	120
TC1	M	0.5~1.0	4T	100
		>1.0~2.0	5T	70

